

aramcoPRIMA[®]

Test	Unit	Method	aramcoPRIMA [®] 500
Group II			Ulsan
Appearance		Visual	C&B
Kinematic Viscosity @ 40°C	cSt	D 445	96.4
Kinematic Viscosity @ 100°C	cSt	D 445	11.3
Viscosity Index		D 2270	104
Saturates	wt%	D 2007	99
Sulfur	wt ppm	D2622	2 [‡]
Noack Volatility	w% (Procedure B)	D 5800	6.9
CCS Viscosity @ -20°C	mPa-s	D 5293	14,550
CCS Viscosity @ -25°C	mPa-s	D 5293	26,000
Pour Point	°C	D 97	-18
Brookfield @ -40°C		D 2983	
Density @ 15°C	Kg/L	D 4052	0.8720
Saybolt Color	°C	D 156	+30
Color ASTM	°C	D 1500	L0.5
Flash Point COC	°C	D 92	240
Copper Corrosion 100°C 3hrs		D 130	1b
Total Acid Number	mgKOH/gm	D 974	< 0.01
Aromatics	wt%	D 2007	< 1

Notes: [‡] - D 2622